



Flooring Specifications

Traditional Cherry - Character

Species	Prunus Serotina
Hardness	Janka 950
Thickness	3/4" Solid OR 5/8" Engineered
Coloration	Rich reddish brown natural color variation, with minor lighter sapwood in 10%-15% of plank faces.
Grade Characteristics	Natural grain variation, tight or star-cracked knots, minor open check or cracks on plank face and occasional fillable through holes or voids to 3/4"
Widths	Available 3"-8" RW(3"-5"), RW(3"-6"), RW(4"-7"), RW(5"-8") standard
Lengths	2' to 10'
Moisture Content	6%-9% at production
Millwork	Offset floor-matched tongue and groove and back-relieved End matching available to 10"
Packaging	Hand carry bundles of 4 boards high, 8'-12' long, securely strapped to wood skid of 36"-42" wide x 12'
Eco Status	Harvested from responsibly and sustainably managed Eastern deciduous forests